MIM POWDERS STAINLESS STEEL

TECHNICAL DATA SHEET



SPECIALTY METAL ATOMIZED POWDERS

Recognizing the need for superfine powders for injection molding and other industry requirements, AMETEK Specialty Metal Products (SMP) has developed a proprietary method of producing and processing fine metal powders down to 10 microns. Special size distributions are available on a custom basis.

AUSTENITIC STAINLESS STEEL

316L used in applications which require good corrosion resistance, strength and ductility. Also available 304L and 310L

FERRITIC STAINLESS STEEL


430L ferritic stainless steel combines good magnetic response and some corrosion resistance. Also available 410L, 434L, 409 and 420.

17-4 PH PRECIPITATION HARDENING STAINLESS STEEL

This precipitation hardening grade stainless is used to obtain strength and hardness. It offers better corrosion resistance than 400 series stainless steel. A range of properties and hardness can be achieved through heat treatment.

POWDER MARKETS

- Automotive
- Industrial engineering
- Consumer applications
- |7





Example parts made with the MIM process. This process allows for high volume, complex parts produced in a single step.

MIM POWDERS STAINLESS STEEL





MIM CHEMICAL COMPOSITION

GRADES	NOMINAL CHEMICAL COMPOSITION (%)								
	Fe	Ni	Cr	Мо	C (max)	Cu	Cb	Mn (max)	Si (max)
316L	BAL	10 - 14	16 - 18	2 - 3	0.03	-	-	0.5	1.0
430L	BAL	-	16 - 18	-	0.05	-	-	1.0	1.0
17-4 PH	BAL	3 - 5	15.5 - 17.5	-	0.07	3 - 5	0.15 - 0.45	0.5	1.0
70/30 FeCr	70	-	30	-	-	-	-	-	-

Other elements: total by difference may not exceed 1.0% combined.

MIM PHYSICAL PROPERTIES

GRADES		HARDNESS			
	Ultimate Strength 10 ³ psi	Yield Strengths 10 ³ psi	Elongation %	Density g/cm³	Rockwell
316L	60 - 75	20 - 25	35 - 50	7.6	57 HRB
430L	50 - 60	30 - 35	20 - 25	7.5	65 HRB
17-4 PH	150 - 172	120 - 158	4.0 - 6.0	7.5	33 HRC

AMETEK SMP FINE POWDERS

Metal Injection Molding
Plastics Compounding and Other Applications

GRADES	ADVANCED TESTING	SIZING
17-4 PH 316L 70/30 FeCr 430L Custom Alloys	Microtrac Tap Density Pycnometric Density	Each order is processed per customer specifications. -400 Mesh -500 Mesh -20µm D50 = 20 microns -15µm D50 = 15 microns -10µm D50 = 13 microns

We have process alternatives to match your binder systems.

Call us to discuss options for custom formulation and custom grades and sizing.



1085 Route 519, Eighty Four, PA 15330, United States

www.powderclad.com